

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 298 172 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

02.04.2003 Bulletin 2003/14

(51) Int Cl.7: **C08L 67/02, C08L 67/00,**

F21V 7/00

(21) Application number: **02256640.0**

(22) Date of filing: **25.09.2002**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR**

Designated Extension States:

AL LT LV MK RO SI

• **Willems, Johannes Gerardus Henricus**

4661 MD Halsteren (NL)

• **Van Baal, Harry**

4464 BA Goes (NL)

• **Van Loenen, Erik**

4822 XB Breda (NL)

(30) Priority: **28.09.2001 US 966351**

(71) Applicant: **GENERAL ELECTRIC COMPANY**

Schenectady, NY 12345 (US)

(74) Representative: **Szary, Anne Catherine, Dr. et al**

GE London Patent Operation,

Essex House,

12-13 Essex Street

London WC2R 3AA (GB)

(72) Inventors:

• **Mercx, Franciscus Petrus**

4611 HH Bergen op Zoom (NL)

(54) **Metallized polyester composition**

(57) A metallized molded article composition which comprises a crystallizable polyester resin and a non-blooming polymeric release agent/lubricant composed of olefinic monomeric units.

Description

[0001] This invention relates to a metallized polyester molded article for use in automotive headlamp housings, such as bezels and reflectors

[0002] Direct metallization of automotive headlamp housings, such as bezels and reflectors, is preferred by automotive manufacturers since it significantly reduces production costs. Flawless surface appearance is a critical requirement for direct metallization since even small surface defects are considerably enhanced after metallization. In addition with the advent of hotter lamps and new styling technologies, high heat resistance is becoming increasingly important. Headlamp bezels typically now require heat stability at temperatures above 150°C. At these higher temperatures, rainbow and haze effects may develop on the surface. A rainbow effect is an unwanted color prismatic effect when the metallized part is viewed under an angle of 10 to 90 degrees. A haze effect is a deposit, typically milky white, which dulls the metallized layer. This effect decrease the reflectivity of the metallized surface.

[0003] US Patent No. 3,953,394 to Fox describes alloys of poly(butylene terephthalate) [PBT] and poly(ethylene terephthalate) [PET] containing 1-80% by weight of glass or mineral filler. US Patent No. 4,351,758 to Lu et al. describe PBT and PET mixtures containing 4-65 weight percent of reinforcing agent including mineral fillers and 0.1-20 weight percent of a nucleating agent such as an alkali metal salt with anions that are oxides of elements from Group IV of the Periodic Table, talc and barium sulfate that yield smooth, glossy surfaces and high heat deflection temperatures when molded at temperatures below 110°C. US Patent No. 5,149,734 to Fisher et al. describe compositions consisting essentially of PBT, PET and 50-75 weight percent of barium sulfate filler of particle size ranging from 0.05 to 50 micron for smooth, glossy surface appearance.

[0004] Polyester compositions containing various ingredients including a high level of reinforcing agents can provide the heat resistance required. However, the inclusion of fillers can be detrimental to achieving a smooth surface. Excellent dispersion of filler is very critical to obtain a smooth, flawless surface. Moreover, the use of high filler levels significantly increases the specific gravity of the composition, thereby elevating the cost per unit volume of the product. Hence, it is desirable to provide resins with high heat resistance and low specific gravity without detracting from desirable surface properties that contribute to good appearance and ease of metallization. In addition, it is also desirable to provide resin compositions that do not develop haze and rainbow effects when exposed to high temperatures.

[0005] The present invention provides a metallized molded polyester article containing a non-blooming mold release agent or lubricant comprising olefinic monomeric units. The molded resin composition provides an excellent surface for direct metallization and develops no or negligible haze and rainbow effects when the metallized part is exposed to heat aging at a temperature of 150°C - 185°C. The non-blooming release agent does not migrate through the metallized layer so that deleterious rainbow and haze effects are avoided. A typical blooming mold release agent, such as pentaerythritol tetrastearate, can migrate through the metallized layer at temperatures on the order of 150 °C resulting in a rainbow or haze effect.

[0006] US patent application No. 09/708/928, filed November 8, 2000 to Talibuddin describes nucleated polyester resins with heat deflection temperatures above 160°C.

[0007] The metallized polyester molded article contains a non-blooming release agents or lubricant based on olefinic monomeric units. A metallized molded resin article, based on the weight of the total resin composition, consists essentially of from about 70 to about 99.9 weight percent, preferably about 90 to about 99.9 weight percent of a polyester crystallizable resin derived from aliphatic, cycloaliphatic diols, or mixtures thereof, containing 2 to 10 carbon atoms and at least one aromatic dicarboxylic acid wherein the aromatic group is a C₆ to C₂₀ aryl radical.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0008] The polyester component includes crystallizable resins derived from aliphatic or cycloaliphatic diols, or mixtures thereof, containing 2 to 10 carbon atoms and at least one aromatic dicarboxylic acid wherein the aromatic group is a C₆ to C₂₀ aryl radical. The polyester is preferably a poly (alkylene terephthalate) and is most preferably poly (butylene terephthalate).


[0009] The "non-blooming" polymeric release agent/lubricant is composed of olefinic monomeric units, e.g. polyolefins, poly-ethylene vinyl acetate (EVA), poly-ethylene ethyl acrylate (EEA). Preferred mold release agents/lubricants have a sufficiently high molecular weight that migration through the metallized layer at temperatures of operation, such as at least 150 °C, will not take place. The most preferred release agent/lubricant is polyethylene (PE). The total amount of release agent/lubricant is preferably from 0.1 to 10% by weight, with the most preferred level being about 0.5 to about 2 percent by weight based on the total weight of the resin component of the article. It is desirable to have a sufficient amount of release agent/ lubricant so that the molded part releases properly from the mold. Typically molding techniques are by injection molding. Increased concentrations of release agent/lubricant may deleteriously affect the adherence of the deposited metallized layer and/or can give rise to mold deposit formation upon long molding cycles and should be avoided.

[0010] Nucleating agents, fillers, primary and/or secondary antioxidants might be added to improve heat resistance, to increase cycle times to reduce production costs or to improve color stability. Additionally other types of release agent might be present as long as they will not give rainbow or haze effects. The metallization is carried out under a vacuum using techniques known in the art. Preferably the metal used is aluminum, particularly for a vehicle lamp. After metallization a protective coating can be applied. Preferably a polydimethylsiloxane coating obtained via plasma polymerization of dimethylsiloxane is applied.

[0011] Preferred nucleating agents can be compounds that are oxides, sulfates, silicates of elements from Group I, II, and IV of the Periodic Table or fibrillar PTFE, and mixtures thereof. The most preferred nucleating agent is talc or barium sulfate with talc being preferred over barium sulfate. Inorganic nucleants can at higher levels also act as a filler, which might be desirable. Besides those nucleating fillers, also other fillers, including those with an aspect ratio >3, e. g. chopped glass fibers, can be used provided that they do not interfere with the surface quality of the metallized part. The level of the nucleating agent in the polymer mixture is 0.0-20 weight percent of the composition, with the preferred level being 0.05 to 5 and the most preferred level being 0.1 to 1 weight percent of the total composition. The average particle size of the nucleating agent should range from 0.1 to 20 micron, with the preferable average particle size being within 0.1 to 10 micron and the most preferred average particle size being within 0.1 to 1 micron. Preferred compositions of the resin component consist essentially of 96, preferably 98 percent by weight polyester based on the weight percent of the resin component.

[0012] The composition of the present invention may include additional components, such as colorants, primary and/or secondary antioxidants, which do not interfere with the previously mentioned desirable properties. Any additional ingredients, other than the polyester, release agent/lubricant and nucleating agent, are desirably present in an amount less than about 5%, preferably less than about 2% by weight based on the total weight of the resin.

[0013] Preferred crystalline thermoplastic polyesters are polyesters derived from an aliphatic or cycloaliphatic diol, or mixtures thereof, containing from 2 to about 10 carbon atoms and at least one aromatic dicarboxylic acid. Preferred polyesters are derived from an aliphatic diol and an aromatic dicarboxylic acid having repeating units of the following general formula:



wherein n is an integer of from 2 to 6. R is a C₆-C₂₀ aryl radical comprising a decarboxylated residue derived from an aromatic dicarboxylic acid.

[0014] Examples of aromatic dicarboxylic acids represented by the decarboxylated residue R are isophthalic or terephthalic acid, 1,2-di(p-carboxyphenyl)ethane, 4,4'-dicarboxydiphenyl ether, 4,4' bisbenzoic acid and mixtures thereof. All of these acids contain at least one aromatic nucleus. Acids containing fused rings can also be present, such as in 1/4-1/5- or 2,6-naphthalene dicarboxylic acids. The preferred dicarboxylic acids are terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid or mixtures thereof.

[0015] Typical polyesters are poly(ethylene terephthalate) ("PET"), and poly(1,4-butylene terephthalate), ("PBT"), poly(ethylene naphthanoate) ("PEN"), poly(butylene naphthanoate), ("PBN"), (polypropylene terephthalate) ("PPT") and poly(cyclohexanedimethanol terephthalate) ("PCT").

[0016] Also contemplated herein are the above polyesters with minor amounts, e.g., from about 0.5 to about 5 percent by weight, of units derived from aliphatic acid and/or aliphatic polyols to form copolyesters. The aliphatic polyols include glycols, such as poly(ethylene glycol). Such polyesters can be made following the teachings of, for example, U.S. Pat. Nos. 2,465,319 and 3,047,539.

[0017] The preferred poly(1,4-butylene terephthalate) resin used in this invention is obtained by polymerizing a glycol component at least 70 mol %, preferably at least 80 mol %, of which consists of tetramethylene glycol and an acid component at least 70 mol %, preferably at least 80 mol %, of which consists of terephthalic acid, or polyester-forming derivatives thereof.

[0018] The polyesters used herein preferably have an intrinsic viscosity of from about 0.4 to about 2.0 dl/g as measured in a 60:40 phenol/tetrachloroethane mixture or similar solvent at 23-30°C.

[0019] Preferred polyesters are crystalline polyesters having a melting point from 150 to 300°C with the most preferred polyester melting between 180 and 250°C.

[0020] The resin mixture may typically comprise additional ingredients which may be added to contribute to desirable properties previously mentioned which include good mechanical properties, color stability, oxidation resistance, good

flame retardancy, good processability, i.e. short molding cycle times, good flow and easy release from a mold, and good metallization properties.

[0021] The method of blending the compositions can be carried out by conventional techniques. One convenient method comprises blending the polyester and nucleating agent, and other ingredients in powder or granular form, extruding the blend under temperatures sufficient to melt the polyester and comminuting into pellets or other suitable shapes. The ingredients are combined in any usual manner, e.g., by dry mixing or by mixing in the melted state in an extruder, in a heated mill or in other mixers.

[0022] Although it is not essential, best results are obtained if the ingredients are pre-compounded, pelletized and then molded. Pre-compounding can be carried out in conventional equipment. For example the polyester resin and other additives can be added to the throat of a single screw extruder having a mixing screw with a long transition section to ensure proper melting. On the other hand, a twin screw extrusion machine can be fed with resins and additives at the feed port at the throat or down stream. Other compounding variations are within the scope of this invention.

[0023] The pre-compounded composition can be extruded and cut or chopped into molding compounds, such as conventional granules, pellets, etc. by standard techniques. The granulate is molded into parts using standard molding techniques and conditions.

EXAMPLES

Examples 1-7

[0024] The components of the formulations presented in Table 1 were tumbled blended and then extruded on a WP25 twin-screw extruder equipped with a vacuum vent. A processing profile of 250-265°C from feed-zone to die-head was employed. The compositions were dried at 110-120 °C for 2- 4 hours and then injection molded into a 120 x 50 x 3 mm plaque on a 100 tons Netstal injection molding machine with a barrel set temperature of 240 - 260 °C. Other processing settings were: Mold temperature 50 °C, 20 mm/s injection speed (resulting in a injection time of approx. 1.44 seconds), 400 bars of after pressure during 5 seconds and 5 bars of hydraulic backpressure. All of these settings resulted in a cycle time of about 25.3 seconds, injection pressure of \pm 800 bars and a residence time of 3.4 minutes. The plaques molded from Comparative example A and B and Examples 1-7 under the molding conditions described above were metallized with aluminum using a vacuum deposition process. After the metallization process, a protective transparent coating of polydimethylsiloxane was applied via plasma polymerization of dimethylsiloxane.

TABLE 1

Example	A*	B*	1	2	3	4	5
Polyester ^a	59.6	59.35	59.5	59.0	58.75	59.5	59
Polyester ^b	40	40	40	40	40	40	40
Pentaerythritol							
Tetratearate ^c	0.4	0.4					
Polyethylene ^d			0.5	1.0	1.0		
Poly-ethylene ethyl						0.5	1.0
acrylate ^e							
Talc ^f		0.25			0.25		
Antioxidant 1010 ^g							
PEPQ ^h							
Total	100	100	100	100	100	100	100

Example	6	7
Polyester ^a	58.9	58.75
Polyester ^b	40	40
Pentaerythritol		
Tetratearate ^c		
Polyethylene ^d	1	1
Poly-ethylene ethyl		
acrylate ^e		
Talc ^f		
Antioxidant 1010 ^g	0.1	
PEPQ ^h		0.25
Total	100	100

a = Poly(1,4-butylene terephthalate), "VALOX", 8500 poise General Electric Company

b = Poly(1,4-butylene terephthalate), "VALOX", 700 poise General Electric Company

c = PETS G from Faci

d = Stamylan LD from DSM

e = Elvaloy 2715AC from Dupont

f = Microtuff AG609 from Keyser & Mackay

g = Anox 20 from Great Lakes Chemical

h = Sandostab PEPQ from Clariant

* = Comparative Example

Example 8-12

[0025] The examples 8-12 and comparative example C (table 2) were prepared in the same way as described above

for examples 1-7 and comparative examples A and B.

TABLE 2

Example	C*	8	9	10	11	12
Polyester ^a	58.1381 58.5381	58.2381	59.5	57.9131	57.7881	
Polyester ^b	40	40	40	40	40	40
Pentaerythritol						
Tetrastearate ^c	0.4					
Polyethylene ^d		0.5	0.5	0.75	0.75	1.0
Talc ^e	0.25	0.05	0.25	0.125	0.25	0.25
Antioxidant 1010 ^f	0.06	0.06	0.06	0.06	0.06	0.06
TiO ₂ ^g	1.1	1.1	1.1	1.1	1.1	1.1
Pigment blue ^h	0.0001 0.0001	0.0001	0.0001	0.0001	0.0001	
Pigment yellow 53 ⁱ	0.05	0.05	0.05	0.05	0.05	0.05
Carbon blacks ^j	0.0018 0.0018	0.0018	0.0018	0.0018	0.0018	
Total	100	100	100	100	100	100

a = Poly(1,4-butylene terephthalate), "VALOX", 8500 poise General Electric Company

b = Poly(1,4-butylene terephthalate), "VALOX", 700 poise General Electric Company

c = PETS G from Faci

d = Stamylan LD from DSM

e = Microtuff AG609 from Keyser&Mackay

f = Anox 20 from Great Lakes Chemical

g = Rutile TiO₂ from Huntsman(Tioxide)

h = Ultramarine Blue from Holliday Pigments Ltd.

i = Pigment Yellow 53 from BASF

j = Pigment Black 7 from Cabot

* = Comparative Example

Results from Examples 1-7

[0026] Metallized plaques (including protective PDMS coating) were visually inspected after heat treatment at 160°C for 1 hour and judged on haze and rainbow effects. The following rating was applied:

1= severe rainbow or haze

2= moderate or slight rainbow or haze

3= no detectable or insignificant traces of rainbow or haze.

Example	A	B	1	2	3	4	5	6	7
Haze	1	1	3	3	3	3	3	3	3
Rainbow	2	1	3	3	3	3	3	3	3

[0027] Examples 1-7, which contain polyethylene (PE) or ethylene ethyl acrylate show no detectable or insignificant traces of rainbow and haze compared to the comparative examples A and B, which contain pentaerythritol tetrastearate (PETS) as release agent. PE is particularly effective in reducing the haze and rainbow phenomena when nucleated formulations are used as can be inferred upon comparing examples 3 and 4 to the comparative example B. Interestingly the inclusion of primary antioxidants like 1010 and secondary stabilizers like PEPQ does not negatively affect the surface appearance (haze and rainbow) after metallization and heat treatment.

Results from Examples 8-12

[0028] Metallized plaques (including protective PDMS coating) were visually inspected after heat treatment at 160°C

EP 1 298 172 A1

for 1 hour and judged on haze and rainbow effects. The following rating was applied:

- 1= severe rainbow or haze
- 2= moderate or slight rainbow or haze
- 3= no detectable or insignificant traces of rainbow or haze.

Example	C	8	9	10	11	12
Haze	1	3	3	3	3	3
Rainbow	1	3	3	3	3	3

[0029] Examples 8-12, containing polyethylene (PE) as release/lubricant as well as talc nucleation, show no detectable or insignificant rainbow and haze compared to the comparative example C based on PETS and talc nucleation. Interestingly, the inclusion of the color package to render the base material light grey, does not adversely affect the surface appearance (haze and rainbow) after metallization and heat treatment.

[0030] The above examples clearly show that polyester resins can be used to produce high heat, directly metallizable molded products that develop no or negligible rainbow and haze effects after heat treatment at 160°C, when release/lubricant based on polyolefin moieties are used.

Claims

1. A metallized molded resin article, consisting essentially of

a) from about 70 to about 99.9 weight percent, based on the total weight of the resin composition, of a crystallizable polyester resin derived from aliphatic or cycloaliphatic diols, or mixtures thereof, containing 2 to 10 carbon atoms and at least one aromatic dicarboxylic acid wherein the aromatic group is a C₆ to C₂₀ aryl radical

b) a non-blooming polymeric release agent/lubricant composed of olefinic monomeric units

c) optionally, from 0 to about 20 percent by weight nucleants and/or fillers,

d) less than 5% by weight additional ingredients based on the total weight of the resin composition,

a portion of the surface of said article being metallized.

2. A metallized molded resin article according to claim 1 wherein said release agent/lubricant is non-blooming when the metallized molded resin article is subject to aging at temperature of 150 -185 °C.

3. A metallized molded resin article according to claim 1 or claim 2 wherein said mold release agent/lubricant is selected from the group consisting of polyethylene, poly-ethylene vinyl acetate (EVA) or poly-ethylene ethyl acrylate (EEA) or mixtures thereof.

4. A metallized molded resin article according to any preceding claim wherein the release agent/lubricant is present in a sufficiently high weight percent that sufficient release upon molding is obtained and present in a sufficiently low weight percent that good metal adhesion takes place upon metallization and/or that no mold deposit formation takes place upon long molding cycles.

5. A metallized molded resin article according to any preceding claim wherein the release agent/lubricant is present in an amount from about 0.3 to about 2 percent by weight based on the total weight of the resin component of the article.

6. A metallized molded resin article according to any preceding claim wherein the metallization is carried out under a vacuum.

7. A metallized molded resin article according to any preceding claim wherein the metallized article comprises aluminum.

8. A metallized molded resin article according to any preceding claim wherein the metallized article comprises a reflective vehicle lamp part.
9. A metallized molded resin article according to any preceding claim wherein the crystallizable polyester resin component is selected from the group consisting essentially of poly(ethylene terephthalate), poly(1,4-butylene terephthalate), poly(ethylene naphthanoate), poly(butylene naphthanoate), poly(cyclohexane dimethanol terephthalate), (polypropylene terephthalate) and mixtures thereof.
10. A process for making a metallized molded resin article comprising the steps of a) forming a resin mixture consisting essentially from about 70 to about 99.9 weight percent, based on the total weight of the resin composition, of a crystallizable polyester resin derived from aliphatic or cycloaliphatic diols, or mixtures thereof, containing 2 to 10 carbon atoms and at least one aromatic dicarboxylic acid wherein the aromatic group is a C₆ to C₂₀ aryl radical, a polymeric release agent / lubricant comprising olefinic monomeric units, and the remaining amount consisting essentially of one or more nucleants and less than 5% by weight additional ingredients based on the total weight of the resin composition; b) molding said resin mixture in a mold, and c) metallizing a portion of the surface of said article.

EP 1 298 172 A1

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 25 6640

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (In I.C.I.7)
X	US 4 268 570 A (IMANAKA HIROSHI ET AL) 19 May 1981 (1981-05-19)	1,2,4, 6-10	C08L67/02 C08L67/00 F21V7/00
Y	* column 1, line 42 - column 1, line 63 * * column 2, line 32 - column 5, line 30 *	3,5	
Y	US 4 699 942 A (WEAVER JAMES C ET AL) 13 October 1987 (1987-10-13)	3,5	
A	* column 1, line 57 - column 3, line 32; claims 1-4,7-9 *	1,2,4, 6-10	
A	US 4 487 862 A (MARUYA KAZUO) 11 December 1984 (1984-12-11) * column 3, line 17 - column 3, line 23 * * column 5, line 4 - column 5, line 15 * * column 6, line 54 - column 6, line 56 * * column 8, line 15 - column 9, line 14 *	1-10	
A	DE 16 94 198 A (HOECHST AG) 21 October 1971 (1971-10-21) * the whole document *	1-10	
A	US 6 165 610 A (DE LA CRUZ DANILO O ET AL) 26 December 2000 (2000-12-26) * the whole document *	1-10	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C08L F21V
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 14 January 2003	Examiner Zeslawski, W
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPC FORM 1503 (03.02) (P04C01)

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 02 25 6640

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

14-01-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4268570	A	19-05-1981	JP 55009873 A	24-01-1980
			JP 58054668 B	06-12-1983
			DE 2927177 A1	17-01-1980
US 4699942	A	13-10-1987	NONE	
US 4487862	A	11-12-1984	JP 58157802 A	20-09-1983
			JP 58157803 A	20-09-1983
			DE 3308204 A1	15-09-1983
			FR 2523141 A1	16-09-1983
			GB 2117386 A ,B	12-10-1983
DE 1694198	A	21-10-1971	DE 1694198 A1	21-10-1971
US 6165610	A	26-12-2000	NONE	